

WARWICK - PPG

878S/HE

<u>BASECOAT:</u>			
Envirobase	Nozzle Size	1.0mm	1.4mm
	Air Pressure	27psi	29psi
	Air Consumption	3.7cfm	3.9cfm

<u>BASECOAT:</u>			
BC	Nozzle Size	1.0mm	1.4mm
	Air Pressure	27psi	29psi
	Air Consumption	3.7cfm	3.9psi

<u>SINGLE STAGE:</u>			
DG DGLV	Nozzle Size	1.0mm	1.4mm
	Air Pressure	29psi	29psi
	Air Consumption	3.7cfm	3.9cfm

<u>CLEARCOATS:</u>			
D890 D893 D894 D8101	Nozzle Size	1.0mm	1.4mm
	Air Pressure	29psi	29psi
	Air Consumption	3.7cfm	3.9cfm

<u>PRIMERS:</u>			
DTM D824 D831	Nozzle Size	1.0mm	1.4mm
	Air Pressure	29psi	29psi
	Air Consumption	3.7cfm	3.9cfm

<u>PRIMER SURFACERS:</u>			
DTM D822 D825 D839 D848 D860	Nozzle Size	1.0mm	1.4mm
	Air Pressure	29psi	29psi
	Air Consumption	3.7cfm	3.9cfm

<u>PRIMER SEALERS:</u>			
DTM D825/Sealer D839/Sealer D859 D891 D8070-75	Nozzle Size	1.0mm	1.4mm
	Air Pressure	29psi	29psi
	Air Consumption	3.7cfm	3.9cfm

NOTE: PPG Industries does NOT endorse any particular type or brand of application equipment. The above recommendations are only a general reference and should be used solely as a starting point. Your particular spray environment and application technique may require slight adjustments. All equipment was tested using full trigger" during application with regulators approved by the spray gun manufacturer